

Kurulma
Automotive Refinish **2K**

Primer Surfacer 2K 4:1



High solid
and hiding ability



Good solvent
resistant



Easy to sand




“Applying a primer before the topcoat improves adhesion between the substrate and the topcoat”

Multi-colors for appropriate matching with color coat




HOW TO USE
• อยากรู้ • 3818 • 3818



WHITE



GREY



BLACK

The Color Patterns on this card are approximate only



1 GL

1/4 GL

Kuruma Primer Surfacer 2K 4:1



Description	- High solid and hiding ability - Good solvent resistance - Easy to sand - Multi-colors for appropriate matching with color coat (Gray, White, Black)
Surface Preparation	Clean surface to be dry and without wax, grease, dust and contaminants
Mixing Ratio	Kuruma Primer Surfacer : Hardener = 100 : 16 by weight or 100 : 25 by volume and dilute with Kuruma Thinner No.20 at 20 - 30 % for suitable application
Pot Life at 30°C	1 hours after complete mixing
Spray Viscosity at 30°C	16.0 - 18.0 sec / Ford cup No.4
Spray Gun Setting	Gravity Feed Spraying nozzle : 1.4 - 1.8 mm. Spraying air pressure : 1.5 - 2.0 bar
No. of Coats	2 Full coats
Dry Film Thickness	50 to 60 Microns
Flash Time	2 - 5 minutes flash time between coats
Drying Time at 30°C	Touch Dry : 5 - 8 mins. Dry to sand : 45 - 60 mins.
Package Size	Part A : 3 L (4 can / carton), Part A : 1 L (12 can / carton) Part B : 0.75 L (4 can / carton), Part B : 0.25 L (12 can / carton)

Safety and Disposal	1. For full Health and Safety information, please refer to Material Safety Data Sheet 2. Observe the precautionary notices displayed on the container 3. Goggles and suitable protective equipment must be worn while using these products 4. Good ventilation must be provided in the working environment
----------------------------	---

คุณลักษณะ	- เนื้อสีมาก พ่นกลบรอยได้ดี - พิสูจน์สีทนทานต่อตัวทำละลายได้ดี - ชัดแตงง่าย - มีเฉดสีให้เลือกใช้ตามความเหมาะสม (ขาว, เทา, ดำ)
การเตรียมพื้น	ทำความสะอาดพื้นผิวให้แห้งสะอาด ปราศจากคราบไขมัน ผื่นละออง และสิ่งแปลกปลอมอื่นๆ
อัตราส่วนผสม	คูรูม่า สีพื้นรองพื้น : ฮาร์ดเด็นเนออร์ = 100 : 16 โดยน้ำหนัก หรือ 100 : 25 โดยปริมาตร และเจือจางด้วย คูรูม่า ทินเนอร์ เบอร์ 20 ไม่นเกิน 20 - 30 % เพื่อให้เหมาะสมกับการพ่น
อายุการใช้งาน ที่อุณหภูมิ 30 °C	ผสมแล้วควรใช้ให้หมดภายใน 1 ชั่วโมง
ความหนืดในการพ่น ที่อุณหภูมิ 30 °C	16.0 - 18.0 วินาที / ถ้วยฟอร์ด เบอร์ 4
การตั้งค่าปืนพ่นสี	พ่นแบบปกติ ขนาดหัวปืนพ่นสี : 1.4 - 1.8 มม. แรงดันลมที่ปืนพ่นสี : 1.5 - 2.0 บาร์
จำนวนรอบที่พ่น	แนะนำให้พ่น 2 เที่ยวเต็ม
ความหนาฟิล์มเมื่อแห้ง	50 - 60 ไมครอน
พักระหว่างเที่ยว	2 - 5 นาที / เที่ยว
ระยะเวลาในการแห้งตัว ที่อุณหภูมิ 30 °C	แห้งผิว : 5 - 8 นาที แห้งชัด : 45 - 60 นาที
ขนาดบรรจุ	ส่วน A : 3 ลิตร (4 กระป๋อง / ลัง), ส่วน A : 1 ลิตร (12 กระป๋อง / ลัง) ส่วน B : 0.75 ลิตร (4 กระป๋อง / ลัง), ส่วน B : 0.25 ลิตร (12 กระป๋อง / ลัง)

ความปลอดภัยในการใช้และการจัดการอุปกรณ์	1. เพื่อความปลอดภัยในสุขภาพ โปรดศึกษาและปฏิบัติตามเอกสารความปลอดภัยอย่างเคร่งครัด 2. โปรดสังเกตและอ่านคำเตือนบนบรรจุภัณฑ์ทุกครั้งก่อนการใช้งาน 3. ระหว่างปฏิบัติงาน ควรสวมใส่อุปกรณ์ป้องกันที่เหมาะสมทุกครั้งที่เกี่ยวข้องกับผลิตภัณฑ์ที่มีส่วนประกอบของสารเคมี 4. บริเวณที่มีการปฏิบัติงาน ควรใช้อากาศถ่ายเทสะดวก ไม่มีกรังฟุ้งกระจายของไอพ่นหรือสเปรย์
---	---



TOAPC ลีนซ์ซ่อมรถยนต์และกระดานทราย @toapc TOAPC Official toapc_kuruma

